

MIGRATION OF CERTAIN ELEMENTS according to UNE-EN 71-3 SAFETY OF TOYS

1.- SAMPLE DESCRIPTION.

- AUTOADHESIVO CG-349

2.- MANUFACTURER

- TORRASPAPEL, S.A.

3.- TEST METHODOLOGY.

Sample preparation and metals extraction have been carried out according to UNE-EN 71-3: 1994 standard method.

Determinations of antimony (Sb), arsenic (As), barium (Ba), cadmium (Cd), chromium (Cr), lead (Pb) and selenium (Se) have been made by ICP-induced plasma spectrometry while mercury (Hg) has been analysed by atomic absorption technique.

4.- RESULTS.

Testing date: 25/05/2007

Metals	Content (ppm)	Maximum allowed value (ppm)	Detection limit
Antimony	< 5,0	60	5,0
Arsenic	< 6,3	25	6,3
Barium	156,7 ± 91,9	1000	43,8
Cadmium	< 4,4	75	4,4
Chromium	< 4,4	60	4,4
Lead	< 8,8	90	8,8
Selenium	17,5 ± 4,0	500	5,0
Mercury	<0,003	60	0,003

Membre de:



IT

XARXA DE CENTRES
DE SUPORT
A LA INNOVACIÓ
TECNOLÒGICA

CIDEM

R75.1-07.1 Rev.:01



ACREDITAT PER ENAC

These results are expressed in mg element/Kg of material. Maximum values are those allowed in UNE EN 71-3 standard for these specific metals all them referred to soluble part

Results of migration indicate that mostly all of metals present a concentration under detection limit. In no case, maximum values allowed are surpassed.

5. - CONCLUSIONS.

Sample analysed, referred as AUTOADHESIVO CG-349 **is agree** with UNE-EN 71-3 on safety of toys. Part 3: Migration of certain elements.

Service responsible



Mª Angels Pèlach
Dr. Chemistry Science

Laboratory responsible



Laura Barberà Rodríguez
Chemistry Science Degree