

English

Creaset Tobacco

Coated 1side developed for soft packages of cigarettes

Property		Units	Tolerance	
Substance		gsm	± 4%	90
Thickness	ISO 534	µm	± 7%	74
Whiteness CIE D65 /10°	ISO 11475	%	± 3	117
Smoothness Bekk	ISO 5627	s	-200	1300
Cobb (uncoated side)	ISO 535	g/m ²	± 4	24
Opacity	ISO 2471:1977	%	-2	88,5
Paper gloss	TAPPI T480 om-92	%	± 5	72
Relative humidity	TAPPI T502 om-89	%	± 7	48

- Last updated: **25/5/2010**
- Values are subject to change without notice.

Castellano

Creaset Tobacco

Estucado 1 cara desarrollado para paquetes blandos de cigarrillos

Propiedad		Unidades	Tolerancia	
Gramaje		gsm	± 4%	90
Calibre	ISO 534	µm	± 7%	74
Blancura CIE D65 /10°	ISO 11475	%	± 3	117
Lisura Bekk	ISO 5627	s	-200	1300
Cobb (dorso)	ISO 535	g/m ²	± 4	24
Opacidad	ISO 2471:1977	%	-2	88,5
Brillo de papel	TAPPI T480 om-92	%	± 5	72
Humedad relativa	TAPPI T502 om-89	%	± 7	48

- Última actualización: **25/5/2010**
- Los valores están sujetos a cambio sin aviso previo.

Français

Creaset Tobacco

Couché une face pour paquets souples de cigarettes

Propriété		Unités	Tolérance	
Grammage		gsm	± 4%	90
Épaisseur	ISO 534	µm	± 7%	74
Blancheur CIE D65 /10°	ISO 11475	%	± 3	117
Lissé Bekk	ISO 5627	s	-200	1300
Cobb (non couché face)	ISO 535	g/m ²	± 4	24
Opacité	ISO 2471:1977	%	-2	88,5
Brillance Papier	TAPPI T480 om-92	%	± 5	72
Humidité relative	TAPPI T502 om-89	%	± 7	48

- Dernière actualisation: **25/5/2010**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português

Creaset Tobacco

Couché 1 Face desenvolvido para embalagens de cigarros

Propriedade		Unidade	Tolerância	
Gramagem		gsm	± 4%	90
Calibre	ISO 534	µm	± 7%	74
Brancura CIE D65 /10°	ISO 11475	%	± 3	117
Lisura Bekk	ISO 5627	s	-200	1300
Cobb (dorso)	ISO 535	g/m ²	± 4	24
Opacidade	ISO 2471:1977	%	-2	88,5
Brilho do papel	TAPPI T480 om-92	%	± 5	72
Humidade relativa	TAPPI T502 om-89	%	± 7	48

- Última actualização: **25/5/2010**
- Os valores estão sujeitos a mudanças sem pré-aviso.