

English

CreatorMatt

2 Side Coated Matt

Property			Units	Tolerance	80	90	100	115	125	130	135	150	170
Substance	ISO 536	TAPPI T410	gsm	± 4%	80	90	100	115	125	130	135	150	170
Thickness	ISO 534	TAPPI T411	µm	± 4%	74	81	91	105	106	111	116	132	150
Whiteness CIE	ISO 11475		%	± 3	119	119	119	119	120	120	120	120	120
Opacity	ISO 2471	TAPPI T519	%	-2.0	90,0	92,0	93,5	95,0	94,5	95,0	95,5	96,0	97,0
Roughness Bendtsen	ISO 8791-2		ml/min	≤100	70	70	80	80	-	-	-	-	-
Smoothness Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	200	200	150	130	130
Relative Humidity		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48

- Last updated: **07-05-10**
- Values are subject to change without notice.

Español

CreatorMatt

Estucado 2 Caras Mate

Propiedad			Unidades	Tolerancia	80	90	100	115	125	130	135	150	170
Gramaje	ISO 536	TAPPI T410	g/m ²	± 4%	80	90	100	115	125	130	135	150	170
Calibre	ISO 534	TAPPI T411	µm	± 4%	74	81	91	105	106	111	116	132	150
Blancura CIE	ISO 11475		%	± 3	119	119	119	119	120	120	120	120	120
Opacidad	ISO 2471	TAPPI T519	%	-2.0	90,0	92,0	93,5	95,0	94,5	95,0	95,5	96,0	97,0
Rugosidad Bendtsen	ISO 8791-2		ml/min	≤100	70	70	80	80	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	200	200	150	130	130
Humedad relativa		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48

- Última actualización: **07-05-10**
- Los valores están sujetos a cambio sin aviso previo.

Français

CreatorMatt

Couché 2 Faces Mat

Propriété			Unités	Tolérance	80	90	100	115	125	130	135	150	170
Grammage	ISO 536	TAPPI T410	g/m ²	± 4%	80	90	100	115	125	130	135	150	170
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	74	81	91	105	106	111	116	132	150
Blancheur CIE W	ISO 11475		%	± 3	119	119	119	119	120	120	120	120	120
Opacité	ISO 2471	TAPPI T519	%	-2.0	90,0	92,0	93,5	95,0	94,5	95,0	95,5	96,0	97,0
Rugosité Bendtsen	ISO 8791-2		ml/min	≤100	70	70	80	80	-	-	-	-	-
Lissé Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	200	200	150	130	130
Humidité relative		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48

- Dernière actualisation: **07-05-10**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português

CreatorMatt

Couché 2 Faces Mate

Propriedade			Unidade	Tolerância	80	90	100	115	125	130	135	150	170
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	80	90	100	115	125	130	135	150	170
Calibre	ISO 534	TAPPI T411	µm	± 4%	74	81	91	105	106	111	116	132	150
Brancura CIE	ISO 11475		%	± 3	119	119	119	119	120	120	120	120	120
Opacidade	ISO 2471	TAPPI T519	%	-2.0	90,0	92,0	93,5	95,0	94,5	95,0	95,5	96,0	97,0
Aspereza Bendtsen	ISO 8791-2		ml/min	≤100	70	70	80	80	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	200	200	150	130	130
Humidade relativa		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48

- Última actualização: **07-05-10**
- Os valores estão sujeitos a mudanças sem pré-aviso.