

English

CreatorSatin Polaris

Heat Set Web Offset / Reels. 2 Side Coated Silk

Property			Units	Tolerance												
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	125	130	135	150	170				
Thickness	ISO 534	TAPPI T411	µm	± 4%	78	87	99	105	109	113	129	146				
Whiteness CIE	ISO 11475		%	± 3	119	119	119	120	120	120	120	120				
Opacity	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	94,5	94,0	96,0	96,5	97,0	97,5				
Smoothness Bekk	ISO 5627	TAPPI T475	s		300	300	300	300	300	250	250	250				
Relative Humidity		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48				

- Last updated: **07-05-10**
- Values are subject to change without notice.

Español

CreatorSatin Polaris

Impresión Roto-Offset / Bobinas. Estucado 2 Caras Semimate

Propiedad			Unidades	Tolerancia												
Gramaje	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	125	130	135	150	170				
Calibre	ISO 534	TAPPI T411	µm	± 4%	78	87	99	105	109	113	129	146				
Blancura CIE	ISO 11475		%	± 3	119	119	119	120	120	120	120	120				
Opacidad	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	94,5	94,0	96,0	96,5	97,0	97,5				
Lisura Bekk	ISO 5627	TAPPI T475	s		300	300	300	300	300	250	250	250				
Humedad relativa		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48				

- Última actualización: **07-05-10**
- Los valores están sujetos a cambio sin aviso previo.

Français

CreatorSatin Polaris

Impression Roto-Offset / Bobines. Couché 2 Faces Demi-mat

Propriété			Unités	Tolérance												
Grammage	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	125	130	135	150	170				
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	78	87	99	105	109	113	129	146				
Blancheur CIE W	ISO 11475		%	± 3	119	119	119	120	120	120	120	120				
Opacité	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	94,5	94,0	96,0	96,5	97,0	97,5				
Lissé Bekk	ISO 5627	TAPPI T475	s		300	300	300	300	300	250	250	250				
Humidité relative		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48				

- Dernière actualisation: **07-05-10**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português

CreatorSatin Polaris

Impressão Roto-Offset / Bobinas. Couché 2 Faces Semi-mate

Propriedade			Unidade	Tolerância												
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	125	130	135	150	170				
Calibre	ISO 534	TAPPI T411	µm	± 4%	78	87	99	105	109	113	129	146				
Brancura CIE	ISO 11475		%	± 3	119	119	119	120	120	120	120	120				
Opacidade	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	94,5	94,0	96,0	96,5	97,0	97,5				
Lisura Bekk	ISO 5627	TAPPI T475	s		300	300	300	300	300	250	250	250				
Humidade relativa		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48				

- Última actualização: **07-05-10**
- Os valores estão sujeitos a mudanças sem pré-aviso.