

Property	ISO	TAPPI	Units	Tolerance	Text				Cover		
					60#	70#	80#	100#	80#	100#	130#
Substance	ISO 536	TAPPI T410	gsm	± 4%	89	104	118	148	216	270	351
Thickness (pt.)	ISO 534	TAPPI T411	pt.	± 4%	3,1	3,5	4,0	5,1	7,7	10,4	14,1
Thickness (µm)	ISO 534	TAPPI T411	µm	± 4%	79	90	102	129	196	263	358
Brightness R457	ISO 2470-2	-	%	± 2	95,7	95,7	95,7	95,7	95,7	95,7	95,7
Whiteness CIE	ISO 11475	-	%	± 3	120	120	120	120	120	120	120
Opacity	ISO 2471	TAPPI T519	%	-2.0	92,0	93,5	95,0	97,0	-	-	-
Smoothness Bekk	ISO 5627	TAPPI T475	s	± 40%	220	210	220	200	130	120	100
Relative Humidity	-	TAPPI T502	%	± 7%	50	50	50	50	50	50	50

- Last updated: **06-03-12**
- Values are subject to change without notice.