

English **CreatorStar**

2 Side Coated Gloss

Property			Units	Tolerance	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Substance	ISO 536	TAPPI T410	gsm	± 4%	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Thickness	ISO 534	TAPPI T411	µm	± 4%	64,0	70,0	79,0	90,0	93,0	96,0	100,0	110,0	124,0	140,0	165,0	190,5	202,0	230,0	285,0
Whiteness CIE	ISO 11475		%	± 3	119	119	119	119	122	122	122	122	122	122	122	122	122	122	122
Opacity	ISO 2471	TAPPI T519	%	-2,0	89,5	91,5	93,0	94,5	93,7	94,0	94,5	96,0	97,0	-	-	-	-	-	-
Paper Gloss	ISO 8254-1	TAPPI T480	%	± 5	65	66	67	68	77	77	77	78	76	76	76	76	76	76	76
Smoothness Bekk	ISO 5627	TAPPI T475	s		1200	1200	1100	950	1100	1000	1000	800	800	500	500	400	300	300	200
Relative Humidity		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Last updated: **07-05-10**
- Values are subject to change without notice.

Español **CreatorStar**

Estucado 2 Caras Brillante

Propiedad			Unidades	Tolerancia	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Gramaje	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	TAPPI T411	µm	± 4%	64,0	70,0	79,0	90,0	93,0	96,0	100,0	110,0	124,0	140,0	165,0	190,5	202,0	230,0	285,0
Blancura CIE	ISO 11475		%	± 3	119	119	119	119	122	122	122	122	122	122	122	122	122	122	122
Opacidad	ISO 2471	TAPPI T519	%	-2,0	89,5	91,5	93,0	94,5	93,7	94,0	94,5	96,0	97,0	-	-	-	-	-	-
Brillo de papel	ISO 8254-1	TAPPI T480	%	± 5	65	66	67	68	77	77	77	78	76	76	76	76	76	76	76
Lisura Bekk	ISO 5627	TAPPI T475	s		1200	1200	1100	950	1100	1000	1000	800	800	500	500	400	300	300	200
Humedad relativa		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Última actualización: **07-05-10**
- Los valores están sujetos a cambio sin aviso previo.

Français **CreatorStar**

Couché 2 Faces Brillant

Propriété			Unités	Tolérance	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Grammage	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	64,0	70,0	79,0	90,0	93,0	96,0	100,0	110,0	124,0	140,0	165,0	190,5	202,0	230,0	285,0
Blancheur CIE W	ISO 11475		%	± 3	119	119	119	119	122	122	122	122	122	122	122	122	122	122	122
Opacité	ISO 2471	TAPPI T519	%	-2,0	89,5	91,5	93,0	94,5	93,7	94,0	94,5	96,0	97,0	-	-	-	-	-	-
Brillance du papier	ISO 8254-1	TAPPI T480	%	± 5	65	66	67	68	77	77	77	78	76	76	76	76	76	76	76
Lissé Bekk	ISO 5627	TAPPI T475	s		1200	1200	1100	950	1100	1000	1000	800	800	500	500	400	300	300	200
Humidité relative		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Dernière actualisation: **07-05-10**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português **CreatorStar**

Couché 2 Faces Brilhante

Propriedade			Unidade	Tolerância	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	80	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	TAPPI T411	µm	± 4%	64,0	70,0	79,0	90,0	93,0	96,0	100,0	110,0	124,0	140,0	165,0	190,5	202,0	230,0	285,0
Brancura CIE	ISO 11475		%	± 3	119	119	119	119	122	122	122	122	122	122	122	122	122	122	122
Opacidade	ISO 2471	TAPPI T519	%	-2,0	89,5	91,5	93,0	94,5	93,7	94,0	94,5	96,0	97,0	-	-	-	-	-	-
Brilho do papel	ISO 8254-1	TAPPI T480	%	± 5	65	66	67	68	77	77	77	78	76	76	76	76	76	76	76
Lisura Bekk	ISO 5627	TAPPI T475	s		1200	1200	1100	950	1100	1000	1000	800	800	500	500	400	300	300	200
Humidade relativa		TAPPI T502	%	± 7	48	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Última atualização: **07-05-10**
- Os valores estão sujeitos a mudanças sem pré-aviso.