

2 Side Coated Gloss

Property	ISO 536	TAPPI T410	Units	Tolerance	Text				Cover		
					60#	70#	80#	100#	80#	100#	130#
Substance	ISO 536	TAPPI T410	gsm	± 4%	89	104	118	148	216	270	351
Thickness (pt.)	ISO 534	TAPPI T411	pt.	± 4%	2,7	3,2	3,6	4,5	7,0	9,0	11,2
Thickness (µm)	ISO 534	TAPPI T411	µm	± 4%	69	81	92	114	178	229	285
Brightness R457	ISO 2470-2	-	%	± 2	94,4	94,4	94,4	95,2	95,2	95,2	95,2
Whiteness CIE	ISO 11475	-	%	± 3	119	119	119	119	119	119	119
Opacity	ISO 2471	TAPPI T519	%	-2.0	91,0	93,0	95,0	96,5	-	-	-
Paper Gloss	ISO 8254-1	TAPPI T480	%	± 5	66	67	68	70	70	70	70
Smoothness Bekk	ISO 5627	TAPPI T475	s	± 40%	1200	1000	930	700	550	450	250
Relative Humidity	-	TAPPI T502	%	± 7%	50	50	50	50	50	50	50

- Last updated: **06-03-12**
- Values are subject to change without notice.