

English

CreatorVol Polaris

2 Side Coated Bulky Matt

Property			Units	Tolerance											
Substance	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	110	115	130	135	150	170			
Thickness	ISO 534	TAPPI T411	µm	± 4%	95	105	117	123	142	147	157	182			
Whiteness CIE	ISO 11475		%	± 3	121.4	121.4	121.4	121.4	121.6	121.6	121.6	121.6			
Opacity	ISO 2471	TAPPI T519	%	-2.0	93.0	94.5	95.5	96.0	96.0	96.5	97.5	98.0			
Roughness Bendtsen	ISO 8791-2		ml/min	≤100	100	100	100	100	90	90	-	-			
Smoothness Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	-	-	100	100			
Relative Humidity		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40			

- Last updated: **07-05-10**
- Values are subject to change without notice.

Español

CreatorVol Polaris

Estucado 2 Caras Mate Volumen

Propiedad			Unidades	Tolerancia											
Gramaje	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	110	115	130	135	150	170			
Calibre	ISO 534	TAPPI T411	µm	± 4%	95	105	117	123	142	147	157	182			
Blancura CIE	ISO 11475		%	± 3	121.4	121.4	121.4	121.4	121.6	121.6	121.6	121.6			
Opacidad	ISO 2471	TAPPI T519	%	-2.0	93.0	94.5	95.5	96.0	96.0	96.5	97.5	98.0			
Rugosidad Bendtsen	ISO 8791-2		ml/min	≤100	100	100	100	100	90	90	-	-			
Lisura Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	-	-	100	100			
Humedad relativa		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40			

- Última actualización: **07-05-10**
- Los valores están sujetos a cambio sin aviso previo.

Français

CreatorVol Polaris

Couché 2 Faces Mat à Main

Caractéristique			Unités	Tolérance											
Grammage	ISO 536	TAPPI T410	gr/m ²	± 4%	90	100	110	115	130	135	150	170			
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	95	105	117	123	142	147	157	182			
Blancheur CIE	ISO 11475		%	± 3	121.4	121.4	121.4	121.4	121.6	121.6	121.6	121.6			
Opacité	ISO 2471	TAPPI T519	%	-2.0	93.0	94.5	95.5	96.0	96.0	96.5	97.5	98.0			
Rugosité Bendtsen	ISO 8791-2		ml/min	≤100	100	100	100	100	90	90	-	-			
Lissé Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	-	-	100	100			
Humidité relative		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40			

- Dernière actualisation: **07-05-10**
- Ces valeurs sont sujettes à modification sans avis préalable

Português

CreatorVol Polaris

Couché 2 Faces Mate Volume

Propriedade			Unidade	Tolerância											
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170			
Calibre	ISO 534	TAPPI T411	µm	± 4%	95	105	117	123	142	147	157	182			
Brancura CIE	ISO 11475		%	± 3	121.4	121.4	121.4	121.4	121.6	121.6	121.6	121.6			
Opacidade	ISO 2471	TAPPI T519	%	-2.0	93.0	94.5	95.5	96.0	96.0	96.5	97.5	98.0			
Aspereza Bendtsen	ISO 8791-2		ml/min	≤100	100	100	100	100	90	90	-	-			
Lisura Bekk	ISO 5627	TAPPI T475	s		-	-	-	-	-	-	100	100			
Humidade relativa		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40			

- Última atualização: **07-05-10**
- Os valores estão sujeitos a mudanças sem pré-aviso.